

### ITACONIX® TSIM 710

#### New, uncompromising choice for scale inhibition

Use Itaconix® TSI<sup>TM</sup> 710 to eliminate trade-offs between inhibition performance, environmental safety, and sustainability. This product has excellent mineral and other inorganic scale inhibition for home, institutional and industrial applications. Stable across wide temperature and pH ranges, Itaconix® TSI<sup>TM</sup> 710 is a modified homopolymer of itaconic acid and is 100% bio-based.

#### **Applications**

- Laundry care
- Home care
- Water cooling systems
- Boilers
- Mining
- Oil & gas production and stimulation
- Desalinization
- Membrane anti-fouling
- Water and waste treatment
- Agriculture waste containment sites

#### **Advantages**

- Reduces mineral encrustation
- Superior calcium carbonate inhibitor
- Excellent calcium sulfate inhibitor
- Effective scale inhibitor at low concentration
- High alkalinity and hardness tolerance
- Stable at all pH levels
- · High thermal stability
- 100% bio-based
- Favorable environmental profile


Physical & Chemical Properties		
Chemical class	Sodium polyitaconate	
CAS#	1663489-58-4	
Appearance	Dark orange liquid	
Active	40%	
pH at 10% active	5.6	
Avg. molecular weight (Mw)	2200 g/mole	
Viscosity	45 cP	
Specific gravity	1.22	
Odor	None	
Recommended use	5 to 50 ppm	


# A new class of chemistry for scale prevention

Itaconix® TSI<sup>TM</sup> 710 is a modified homopolymer of itaconic acid that represents a new class of chemistry for inhibiting crystal growth in challenging environments under dynamic pH and temperature conditions.

From detergents to industrial water systems to oilfield production, growth of inorganic crystals leads to scale deposits that are major causes of damage and efficiency loss.

Itaconix® TSI™ 710 offers a breakthrough alternative to common inhibitors such as acrylic acid and aspartic acid polymers for preventing scale formation from inorganic salts.





Data on file, available upon request

# **Excellent stability**

Itaconix® TSI<sup>TM</sup> 710 has excellent stability across broad pH and temperature ranges. It is thermally stable, showing little or no chain scission at 200°C in the pH range of 2 to 14. Due to the absence of labile or hydrolysable groups within its novel chemical structure, it has excellent alkali resistance and is particularly hydrolytically stable over long periods of use.

Itaconix® TSI<sup>TM</sup> 710 is effective in caustic formulations and environments, including concentrated caustic, and in combination with other inhibitors to achieve no data and mineral scale prevention.

Stability with bleach depends on the concentrations of Itaconix® TSI<sup>TM</sup> 710 and bleach, with stability less likely at higher concentrations of either material. Test specific formulations.

#### Stability table

Thermal	Stable up to 200° C
рН	Stable pH 2 to 14
Hydrolytic	Excellent
Bleach	<ul> <li>Unlikely above low concentrations</li> </ul>
	<ul> <li>Recommended to test specific formulations</li> </ul>

# 100% bio-based, environmentally friendly

Itaconix® TSI™ 710 is a unique scale inhibitor option that is both 100% bio-based and poses low environmental burden concern

Current leading scale inhibitors often require formulators to make compromising trade-offs between environmental impact and inhibition performance. Itaconix® TSI<sup>TM</sup> 710 is effective, sustainable and environmentally friendly.

Scale Inhibitor	100% Bio-based	Environmental Concern
Itaconix® TSI™ 710	Yes	Low
Polyacrylate	No	Low
Carboxymethyl inulin	No	Low
Polyaspartic acid	No	Low
Phosphorous based	Yes	High

### Samples available on request

Please e-mail request to: samples@itaconix.com

### To request information on ordering quantities and pricing

Please call: +1 (603) 775-4400 or e-mail: sales@itaconix.com



2 Marin Way, Stratham, New Hampshire 03885, USA • +1 (603) 775-4400

www.itaconix.com

Nothing contained herein grants or extends a license, express or implied, in connection with patents, issued or pending, of the manufacturer or others. The information contained herein is based on the manufacturer's own study and the works of others. The manufacturer makes no warranties, expressed or implied, as to the accuracy, completeness, or adequacy of the information contained herein. The manufacturer shall not be liable (regardless of fault) to the vendee's employees, or anyone for the direct, special or consequential damages arising out of or in connection with the accuracy, completeness, adequacy or furnishing of such information.